

TEST REPORT: 7191035862-01-CHM22-PHS

Date: 12 DEC 2022

Tel: +65 68851275 Fax: +65 67784301

Client's Ref:

Email: songbai.tang@tuv-sud-psb.sg

Note: This report is issued subject to the Testing and Certification Regulations of the TÜV SÜD Group and the General Terms and Conditions of Business of TÜV SÜD PSB Pte Ltd. In addition, this report is governed by the terms set out within this report.



PSB Singapore

Choose certainty.
Add value.

SUBJECT

Measurement of Solar Reflectance, Emittance and Calculation of Solar Reflectance Index (SRI)

CLIENT

PT Citra Megah Selecomindo
Indonesia

Attention: Mr Rahmat Rahardja Ong

SAMPLE SUBMISSION DATE

2 December 2022

DESCRIPTION OF SAMPLE

1 sample named as "Reflecto" was received.

DATE OF ANALYSIS

8 December 2022



Laboratory:
TÜV SÜD PSB Pte. Ltd.
No.1 Science Park Drive
Singapore 118221



LA-2007-0380-A
LA-2007-0381-F
LA-2007-0382-B
LA-2007-0383-G
LA-2007-0384-G
LA-2007-0385-E
LA-2007-0386-C
LA-2010-0464-D

The results reported herein have been performed in accordance with the laboratory's terms of accreditation under the Singapore Accreditation Council - Singapore Laboratory Accreditation Scheme. Tests/Calibrations marked "Not SAC-SINGLAS Accredited" in this Report are not included in the SAC-SINGLAS Accreditation Schedule for our laboratory.

Phone : +65-6885 1333
Fax : +65-6776 8670
E-mail: testing@tuv-sud-psb.sg
www.tuv-sud-psb.sg
Co. Reg : 199002667R

Regional Head Office:
TÜV SÜD Asia Pacific Pte. Ltd.
3 Science Park Drive, #04-01/05
The Franklin, Singapore 118223
TUV®

METHODS OF TEST

The tests and calculation refers to the following three standards:

1) ASTM C 1549 - 09 – Standard Test Method for Determination of Solar Reflectance Near Ambient Temperature Using a Portable Solar Reflectometer.

The sample surface is illuminated diffusely by a tungsten-halogen lamp source and the reflected energy is measured at the specified incidence angle. A solar measurement spectrum is achieved by monitoring the reflected energy with four detectors that cover different wavelength ranges in the solar spectrum. Two additional virtual detectors are added by reading two of the detectors at a second lamp color temperature. A weighted sum of the six detector readings produces a value of solar reflectance. The reflectometer is calibrated using specimens of known solar reflectance.

2) ASTM C 1371 - 04a – Standard Test Method for Determination of Emittance of Materials Near Room Temperature Using a Portable Emissionmeters.

In this test method, a differential thermopile emissometer is used to measure the total hemispherical emittance. The detector portion of the device is heated to 82°C (180°F) so that the sample to be measured does not have to be heated. The detector is designed to have a voltage output that is linear with emittance. The emittance of an unknown surface is measured after the detector has been calibrated with a standard of known emittance, which is maintained at the same temperature as the unknown sample.

3) ASTM E 1980 - 01 – Standard Practice for Calculating Solar Reflectance Index of Horizontal and Low-Sloped Opaque Surfaces.

The steady-state Surface Temperature (T_s) under the sun is strongly correlated to solar reflectivity and thermal emissivity of the surface. This standard covers the calculation of the Surface Temperature and Solar Reflectance Index (SRI) after solar reflectivity and thermal emissivity of the surface are measured. The procedure defines a SRI that measures the relative T_s of a surface with respect to the standard white (SRI = 100) and standard black (SRI = 0) under the standard solar and ambient conditions. Three convective coefficients of 5, 12 and 30 $W.m^{-2}.K^{-1}$ are used for the calculation, corresponding to low-wind (0 to 2 ms^{-1}), medium-wind (2 to 6 ms^{-1}) and high-wind (6 to 10 ms^{-1}) conditions, respectively.

RESULTS

Table 1 Solar reflectance of samples under the air mass 1.5.

Sample Names	Measurement 1	Measurement 2	Measurement 3	Average	Standard Deviation
Reflecto	83.6%	83.1%	83.5%	83.4%	0.26%

Environment temperature of test: 24.2°C

Relative humidity of test: 65 %

Table 2 Emittance values of samples.

Sample Names	Measurement 1	Measurement 2	Measurement 3	Average	Standard Deviation
Reflecto	0.90	0.91	0.92	0.91	0.01

Environment temperature of test: 24.2°C

Relative humidity of test: 65 %

Table 3 Calculated surface temperature (T_s) under different wind conditions.

Sample Name	Surface Temperature (K)		
	Low-wind	Medium-wind	High-wind
Reflecto	319.5	316.1	312.9

Table 4 Calculated Solar Reflectance Index (SRI) under different wind conditions.

Sample Name	Solar Reflectance Index (SRI)		
	Low-wind	Medium-wind	High-wind
Reflecto	114.36	114.42	114.48

Solar Reflectance and Emittance of the sample was about 83.4% and 0.91, respectively, with Solar Reflectance Index in the range of 114.36-114.48.



MR POOI HOW SIANG
TECHNICAL EXECUTIVE



DR TANG SONGBAI
PRODUCT MANAGER
SURFACE ANALYSIS
CHEMICAL & MATERIALS

Please note that this Report is issued under the following terms :

1. This report applies to the sample of the specific product/equipment given at the time of its testing/calibration. The results are not used to indicate or imply that they are applicable to other similar items. In addition, such results must not be used to indicate or imply that TÜV SÜD PSB approves, recommends or endorses the manufacturer, supplier or user of such product/equipment, or that TÜV SÜD PSB in any way "guarantees" the later performance of the product/equipment. Unless otherwise stated in this report, no tests were conducted to determine long term effects of using the specific product/equipment.
2. The sample/s mentioned in this report is/are submitted/supplied/manufactured by the Client. TÜV SÜD PSB therefore assumes no responsibility for the accuracy of information on the brand name, model number, origin of manufacture, consignment or any information supplied.
3. Nothing in this report shall be interpreted to mean that TÜV SÜD PSB has verified or ascertained any endorsement or marks from any other testing authority or bodies that may be found on that sample.
4. This report shall not be reproduced wholly or in parts and no reference shall be made by the Client to TÜV SÜD PSB or to the report or results furnished by TÜV SÜD PSB in any advertisements or sales promotion.
5. Unless otherwise stated, the tests were carried out in TÜV SÜD PSB Pte Ltd, No.1 Science Park Drive Singapore 118221.

December 2022

